

おねじの保証荷重

ねじの呼び	有効断面積	保証荷重 (N) -並目ねじ					
		強度区分					
	mm ²	4.6	4.8	5.8	8.8	10.9	12.9
M 5	14.2	3,200	4,400	5,400	8,230	11,800	13,800
M 6	20.1	4,520	6,230	7,640	11,600	16,700	19,500
M 8	36.6	8,240	11,400	13,900	21,200	30,400	35,500
M 1 0	58.0	13,000	18,000	22,000	33,700	48,100	56,300
M 1 2	84.3	19,000	26,100	32,000	48,900	70,000	81,800
M 1 4	115	25,900	35,600	43,700	66,700	95,500	112,000
M 1 6	157	35,300	48,700	59,700	91,000	130,000	152,000
M 1 8	182	43,200	59,500	73,000	115,000	159,000	186,000
M 2 0	245	55,100	76,000	93,100	147,000	203,000	238,000
M 2 2	303	68,200	93,900	115,000	182,000	252,000	294,000
M 2 4	353	79,400	109,000	134,000	212,000	293,000	342,000
M 3 0	561	126,000	174,000	213,000	337,000	466,000	544,000