

ステンレスボルトの最小引張荷重

ねじの呼び	有効断面積	最小引張荷重 (N) – 並目ねじ	
		強度区分	
	mm ²	A2-50	A2-70
M 5	14.2	7,100	9,940
M 6	20.1	10,050	14,070
M 8	36.6	18,300	25,620
M 1 0	58	29,000	40,600
M 1 2	84.3	42,150	59,010
M 1 4	115	57,500	80,500
M 1 6	157	78,500	109,900
M 1 8	182	91,000	134,400
M 2 0	245	122,500	171,500
M 2 2	303	151,500	212,100
M 2 4	353	176,500	247,100
M 2 7	459	229,500	321,300
M 3 0	561	280,500	392,700
M 3 3	694	347,000	485,800
M 3 6	817	408,500	571,900
M 3 9	976	488,000	683,200